

Vilamul Copolymer Emulsions & Acrylic Polymers

For further information please contact a member of our technical or sales staff.

Vinyl Acetate Copolymer Emulsions

Vilamul Ref No.	Polymer type	Stabilised	Solids %	Viscosity (mPas, Brookfield RV#3) 10rpm	Viscosity (mPas, Brookfield RV#3) 50rpm	pH	S.G.	MFFT ° C	T.G. ° C (Onset)
099	VA / Acrylate	Colloid / Surfactant	51.5 – 53.5	250 - 1000	100 - 750	4.2 – 5.2	1.06	8 - 10	14.5
101	VA / Veova	Colloid / Surfactant	54 - 56	1000 - 3000	400 - 1300	4.0 – 5.0	1.07	10 - 11	19.5
124	VA / Acrylate	Colloid / Surfactant	55.5 – 57.5	2000 - 5000	700 - 1600	4.2 – 5.2	1.07	0	5.5
395	VA / Acrylate	Colloid / Surfactant	54 – 56	2000 - 5000	700 - 1600	4.2 – 5.2	1.07	11 - 12	21.5
605	VA / Veova / Acrylate	Colloid / Surfactant	51.5 – 53.5	1500 - 3000	500 - 1500	4.2 – 5.2	1.06	9 - 11	14.5

Acrylic Polymers

Vilacryl Ref No.	Polymer type	Stabilised	Solids %	Viscosity (mPas, Brookfield RV#3) 10rpm	Viscosity (mPas, Brookfield RV#3) 50rpm	pH	S.G.	MFFT ° C	T.G. ° C (Onset)
800	Acrylic	Colloid / Surfactant	47 - 49	50 - 1000	50 - 500	7.0 – 9.0	1.04	0 - 5	-3.5

TECHSUM 1 215/25

add an extra element

This information is offered in good faith but without guarantee as to the suitability of the product or the suggested uses, nor can it be assumed that the uses will not infringe any patents.



RESINS

Vil Resins Ltd The Valley Bolton UK BL2 2DT
Tel: +44(0)1204 388800 Fax: +44(0)1204 362775

Web: www.vilresins.com Email: enquiries@vilresins.co.uk