

Vilkyd Compliant Resins

We summarise below the resins in our range suitable for use in the manufacture of compliant and low voc coatings. Detailed information on each product is given on the individual technical data sheets and further information is available from our technical staff.

Industrial

Vilkyd Ref No.	%Non-Volatile Content	Solvent	Viscosity @ 25°C (Poise)	%Non-Volatile @ 2 Poise	% Fatty Acid	Fatty Acid Type	Esterifying Alcohol	Principal Uses
157X80	80	Xylene	50-80	55	43	Linoleic Rich	Mixed	Copolymer alkyd for best through drying properties
188X75	75	Xylene	60-90	56	36	Linoleic Rich	Pentaerythritol	Compliant air drying and stoving finishes with excellent water spot resistance

Decorative

Vilkyd Ref No.	%Non-Volatile Content	Solvent	Viscosity @ 25°C (Poise)	%Non-Volatile @ 2 Poise	% Fatty Acid	Fatty Acid Type	Esterifying Alcohol	Principal Uses
211X80	80	Xylene	80-120	56	64	Linoleic Rich	Pentaerythritol	High Solids Coatings
250LA75	75	Low Aromatic	40-50	55	64	Linoleic Rich	Pentaerythritol	Compliant non-yellowing decorative paints with outstanding durability
212LA70	70	Low Aromatic	25-35	53	64	Linoleic Rich	Pentaerythritol	Non-yellowing decorative paints with outstanding durability
251	100	-	15-25	80	74	Linoleic Rich	Pentaerythritol	1. Used with decorative resins to achieve compliancy 2. Pigment dispersions
254	100	-	60-90	74	74	Mixed	Pentaerythritol	Addition to long oil alkyd to help achieve compliancy
258	100	-	30-60	75	78	Linseed	Pentaerythritol	Isophthalic alkyd for pigment dispersions and printing inks
289LA90	90	Low Aromatic	12-18	74	75	Mixed	Mixed	2010 VOC compliant Coatings
298	100	-	12-18	77	74	Linoleic Rich	Pentaerythritol	Used with decorative resins to achieve compliancy
782	100	-	6 – 8 @ 75 C	67	74	Soya	Pentaerythritol	Pigment dispersions
793	100	-	7 – 9 @75 C	63	74	Linseed	TMP	Pigment dispersions

TECHSUM 2 111/21

add an extra element

This information is offered in good faith but without guarantee as to the suitability of the product or the suggested uses, nor can it be assumed that the uses will not infringe any patents.



Vil Resins Ltd The Valley Bolton UK BL2 2DT
Tel: +44(0)1204 388800 Fax: +44(0)1204 362775
Web: www.vilresins.com Email: enquiries@vilresins.co.uk