

Vilkyd Printing Ink Resins

We summarise below the most popular resins used for printing inks. All grades can be offered at different solids contents. For further information please contact a member of our technical or sales staff.

Printing Ink Alkyds

Vilkyd Ref No.	%Non-Volatile Content	Solvent	Viscosity @ 25°C (Poise)	%Non-Volatile @ 2 Poise	% Fatty Acid	Fatty Acid Type	Esterifying Alcohol	Principal Uses
258	100	-	30-50	75	78	Linseed	Pentaerythritol	Isophthalic alkyd for pigment dispersions and printing inks
275	100	-	4.5-6.5 @75C	63	70	Linseed	Pentaerythritol	Printing inks and pigment dispersions
280	100	-	4.5-6.5 @75C	63	70	Linseed	Pentaerythritol	Printing Inks and pigment dispersions
782	100	-	6 - 8 @ 75 C	67	74	Soya	Pentaerythritol	Printing inks and pigment dispersions
793	100	-	7 - 9 @75 C	63	74	Linseed	TMP	Printing inks and pigment dispersions
564DL75	75	DPM	150-200	47	31	Linoleic Rich	TMP	Waterbased inks and decorative paints with outstanding gloss

TECHSUM 6 215/1

add an extra element

This information is offered in good faith but without guarantee as to the suitability of the product or the suggested uses, nor can it be assumed that the uses will not infringe any patents.



Vil Resins Ltd The Valley Bolton UK BL2 2DT
Tel: +44(0)1204 388800 Fax: +44(0)1204 362775
Web: www.vilresins.com Email: enquiries@vilresins.co.uk